


光学特性データ

測定サンプル | シャンティホワイト(CW)

STD. WHITE=	11.695
PG(H)=	0.95
α (H)R=	85.00
α (H)L=	85.00
β (H)R=	0.00
β (H)L=	0.00

(α) = 半値角 (ピークゲインの1/2の値)
 (β) = 1/3値角 (ピークゲインの1/3の値)



HORIZONTAL		
角度	nt	Gs
-80.0°	8.275	0.71
-75.0°	8.604	0.74
-70.0°	8.863	0.76
-65.0°	9.132	0.78
-60.0°	9.38	0.80
-55.0°	9.63	0.82
-50.0°	9.825	0.84
-45.0°	9.891	0.85
-40.0°	10.08	0.87
-35.0°	10.27	0.89
-30.0°	10.49	0.90
-25.0°	10.59	0.91
-20.0°	10.6	0.91
-15.0°	10.6	0.92
-10.0°	10.57	0.93
-5.0°	10.76	0.94
-2.5°	10.98	0.95
+2.5°	10.98	0.94
+5.0°	10.78	0.93
+10.0°	10.55	0.93
+15.0°	10.49	0.92
+20.0°	10.4	0.91
+25.0°	10.21	0.90
+30.0°	10.15	0.90
+35.0°	10.13	0.89
+40.0°	10.02	0.86
+45.0°	9.859	0.84
+50.0°	9.788	0.84
+55.0°	9.605	0.82
+60.0°	9.498	0.81
+65.0°	9.293	0.79
+70.0°	9.06	0.77
+75.0°	8.744	0.75
+80.0°	8.446	0.72