


光学特性データ

測定サンプル | グランビューホワイトマット(GWM)

STD. WHITE =	11.505
PG(H) =	0.97
α (H)R =	85.00
α (H)L =	85.00
β (H)R =	-
β (H)L =	-

(α) = 半値角(ピークゲインの1/2の値)
 (β) = 1/3値角(ピークゲインの1/3の値)



HORIZONTAL		
角度	nt	Gs
-80.0°	7.27	0.65
-75.0°	7.629	0.68
-70.0°	7.888	0.70
-65.0°	8.126	0.72
-60.0°	8.334	0.74
-55.0°	8.543	0.76
-50.0°	8.652	0.77
-45.0°	8.813	0.79
-40.0°	8.962	0.80
-35.0°	9.095	0.81
-30.0°	9.297	0.83
-25.0°	9.517	0.85
-20.0°	9.751	0.87
-15.0°	10.024	0.89
-10.0°	10.226	0.91
-5.0°	10.491	0.93
-2.5°	10.831	0.96
+2.5°	10.844	0.97
+5.0°	10.599	0.94
+10.0°	10.330	0.92
+15.0°	10.090	0.90
+20.0°	9.868	0.88
+25.0°	9.616	0.86
+30.0°	9.375	0.84
+35.0°	9.188	0.82
+40.0°	9.015	0.80
+45.0°	8.868	0.79
+50.0°	8.682	0.77
+55.0°	8.568	0.76
+60.0°	8.405	0.75
+65.0°	8.163	0.73
+70.0°	7.941	0.71
+75.0°	7.661	0.68
+80.0°	7.33	0.65