


# 光学特性データ

測定サンプル | ウルトラマット150(U15)

STD. WHITE=	11.505
PG(H)=	1.50
$\alpha$ (H)R=	75.00
$\alpha$ (H)L=	75.00
$\beta$ (H)R=	85.00
$\beta$ (H)L=	85.00

( $\alpha$ ) = 半値角(ピークゲインの1/2の値)  
 ( $\beta$ ) = 1/3値角(ピークゲインの1/3の値)



HORIZONTAL		
角度	nt	Gs
-80.0°	8.182	0.71
-75.0°	8.629	0.75
-70.0°	8.885	0.77
-65.0°	9.14	0.79
-60.0°	9.268	0.81
-55.0°	9.396	0.82
-50.0°	9.588	0.83
-45.0°	9.716	0.84
-40.0°	9.843	0.86
-35.0°	10.099	0.88
-30.0°	10.419	0.91
-25.0°	10.93	0.95
-20.0°	11.697	1.02
-15.0°	12.847	1.12
-10.0°	14.446	1.26
-5.0°	16.427	1.43
-2.5°	17.306	1.50
+2.5°	16.683	1.45
+5.0°	15.916	1.38
+10.0°	14.126	1.23
+15.0°	12.592	1.09
+20.0°	11.505	1.00
+25.0°	10.802	0.94
+30.0°	10.355	0.90
+35.0°	10.035	0.87
+40.0°	9.84	0.86
+45.0°	9.652	0.84
+50.0°	9.524	0.83
+55.0°	9.385	0.82
+60.0°	9.266	0.81
+65.0°	9.076	0.79
+70.0°	8.82	0.77
+75.0°	8.501	0.74
+80.0°	7.99	0.69