


光学特性データ

測定サンプル | フィルムスクリーン100(FS10)

STD. WHITE =	11.505
PG(H) =	1.00
α (H)R =	45.00
α (H)L =	45.00
β (H)R =	65.00
β (H)L =	65.00

(α) = 半値角(ピークゲインの1/2の値)
 (β) = 1/3値角(ピークゲインの1/3の値)



HORIZONTAL		
角度	nt	Gs
-80.0°	0.959	0.08
-75.0°	2.237	0.19
-70.0°	3.132	0.27
-65.0°	3.579	0.31
-60.0°	3.963	0.34
-55.0°	4.41	0.38
-50.0°	4.922	0.43
-45.0°	5.497	0.48
-40.0°	6.2	0.54
-35.0°	7.031	0.61
-30.0°	7.798	0.68
-25.0°	8.629	0.75
-20.0°	9.46	0.82
-15.0°	10.163	0.88
-10.0°	10.738	0.93
-5.0°	11.122	0.97
-2.5°	11.415	0.99
+2.5°	11.522	1.00
+5.0°	11.186	0.97
+10.0°	10.866	0.94
+15.0°	10.291	0.89
+20.0°	9.588	0.83
+25.0°	8.757	0.76
+30.0°	7.99	0.69
+35.0°	7.095	0.62
+40.0°	6.328	0.55
+45.0°	5.625	0.49
+50.0°	5.05	0.44
+55.0°	4.538	0.39
+60.0°	4.027	0.35
+65.0°	3.643	0.32
+70.0°	3.261	0.28
+75.0°	2.493	0.22
+80.0°	1.278	0.11

