


光学特性データ

測定サンプル | ルミグラス130(LG)

| | |
|-----------------|--------|
| STD. WHITE = | 11.505 |
| PG(H) = | 1.30 |
| α (H)R = | 40.00 |
| α (H)L = | 40.00 |
| β (H)R = | 60.00 |
| β (H)L = | 60.00 |

(α) = 半値角(ピークゲインの1/2の値)
 (β) = 1/3値角(ピークゲインの1/3の値)



| HORIZONTAL | | |
|------------|--------|------|
| 角度 | nt | Gs |
| -80.0° | 1.278 | 0.11 |
| -75.0° | 2.301 | 0.20 |
| -70.0° | 4.155 | 0.36 |
| -65.0° | 4.562 | 0.40 |
| -60.0° | 4.965 | 0.43 |
| -55.0° | 6.072 | 0.53 |
| -50.0° | 6.647 | 0.58 |
| -45.0° | 7.287 | 0.63 |
| -40.0° | 7.464 | 0.65 |
| -35.0° | 9.076 | 0.79 |
| -30.0° | 10.099 | 0.88 |
| -25.0° | 11.314 | 0.98 |
| -20.0° | 12.464 | 1.08 |
| -15.0° | 13.551 | 1.18 |
| -10.0° | 14.254 | 1.24 |
| -5.0° | 14.573 | 1.27 |
| -2.5° | 14.829 | 1.29 |
| +2.5° | 14.957 | 1.30 |
| +5.0° | 14.893 | 1.29 |
| +10.0° | 14.126 | 1.23 |
| +15.0° | 13.039 | 1.13 |
| +20.0° | 11.825 | 1.03 |
| +25.0° | 10.610 | 0.92 |
| +30.0° | 9.524 | 0.83 |
| +35.0° | 8.501 | 0.74 |
| +40.0° | 7.398 | 0.64 |
| +45.0° | 6.903 | 0.60 |
| +50.0° | 6.264 | 0.54 |
| +55.0° | 5.753 | 0.50 |
| +60.0° | 4.965 | 0.43 |
| +65.0° | 4.730 | 0.41 |
| +70.0° | 4.155 | 0.36 |
| +75.0° | 2.940 | 0.26 |
| +80.0° | 1.470 | 0.13 |