

# 光学特性データ

測定サンプル | グランヴェーホワイト(GW)

STD. WHITE=	11.505
PG(H)=	1.00
$\alpha$ (H)R=	85.00
$\alpha$ (H)L=	85.00
$\beta$ (H)R=	-
$\beta$ (H)L=	-

( $\alpha$ ) = 半値角(ピークゲインの1/2の値)  
 ( $\beta$ ) = 1/3値角(ピークゲインの1/3の値)

HORIZONTAL		
角度	nt	Gs
-80.0°	8.437	0.73
-75.0°	8.821	0.77
-70.0°	8.949	0.78
-65.0°	9.14	0.79
-60.0°	9.204	0.80
-55.0°	9.268	0.81
-50.0°	9.332	0.81
-45.0°	9.396	0.82
-40.0°	9.524	0.83
-35.0°	9.588	0.83
-30.0°	9.652	0.84
-25.0°	9.843	0.86
-20.0°	9.971	0.87
-15.0°	10.163	0.88
-10.0°	10.419	0.91
-5.0°	10.802	0.94
-2.5°	11.449	1.00
+2.5°	11.377	0.99
+5.0°	10.738	0.93
+10.0°	10.419	0.91
+15.0°	10.163	0.88
+20.0°	9.971	0.87
+25.0°	9.843	0.86
+30.0°	9.716	0.84
+35.0°	9.652	0.84
+40.0°	9.524	0.83
+45.0°	9.46	0.82
+50.0°	9.332	0.81
+55.0°	9.268	0.81
+60.0°	9.204	0.80
+65.0°	9.076	0.79
+70.0°	8.949	0.78
+75.0°	8.821	0.77
+80.0°	8.309	0.72

