


# 光学特性データ

測定サンプル | ソルベティグラス(SG)

STD. WHITE =	11.465
PG(H) =	1.45
$\alpha$ (H)R =	40.00
$\alpha$ (H)L =	40.00
$\beta$ (H)R =	85.00
$\beta$ (H)L =	85.00

( $\alpha$ ) = 半値角(ピークゲインの1/2の値)  
 ( $\beta$ ) = 1/3値角(ピークゲインの1/3の値)



HORIZONTAL		
角度	nt	Gs
-80.0°	7.616	0.66
-75.0°	7.781	0.68
-70.0°	7.824	0.68
-65.0°	7.82	0.68
-60.0°	7.884	0.69
-55.0°	7.938	0.69
-50.0°	7.93	0.69
-45.0°	7.998	0.70
-40.0°	8.337	0.73
-35.0°	8.471	0.74
-30.0°	8.679	0.76
-25.0°	9.126	0.80
-20.0°	9.742	0.85
-15.0°	10.58	0.92
-10.0°	11.75	1.02
-5.0°	13.98	1.22
-2.5°	16.62	1.45
+2.5°	16.44	1.43
+5.0°	13.71	1.20
+10.0°	11.61	1.01
+15.0°	10.49	0.91
+20.0°	9.681	0.84
+25.0°	9.077	0.79
+30.0°	8.623	0.75
+35.0°	8.451	0.74
+40.0°	8.336	0.73
+45.0°	8.053	0.70
+50.0°	8.01	0.70
+55.0°	8	0.70
+60.0°	7.948	0.69
+65.0°	7.915	0.69
+70.0°	7.906	0.69
+75.0°	7.777	0.68
+80.0°	7.609	0.66